ChemComm

COMMUNICATION



View Article Online

Cite this: Chem. Commun., 2015, 51, 8962

Received 3rd March 2015, Accepted 22nd April 2015

DOI: 10.1039/c5cc01830g

www.rsc.org/chemcomm

NMR crystallography of monovalent cations in inorganic matrixes: Li⁺ siting and the local structure of Li⁺ sites in ferrierites[†]

P. Klein,^{ab} J. Dedecek,^a H. M. Thomas,^a S. R. Whittleton,^a V. Pashkova,^a J. Brus,^c L. Kobera^c and S. Sklenak*^a

 7 Li- 7 Li correlation MAS NMR spectroscopy, interpreted using periodic DFT including molecular dynamics conformational sampling of Li⁺ sites, is employed to obtain the siting of Li⁺ at exchangeable positions of ferrierites and the local structure of these Li⁺ sites. The former is controlled by the Al siting in the zeolite framework.

Zeolites represent the most important group of heterogeneous catalysts widely applied in industry. Besides the Y and USY zeolites of the faujasite structure, silicon-rich zeolites (Si/Al > 8) such as ZSM-5, the beta zeolite, ferrierite, MCM-22, and mordenite exhibit the highest industrial impact.¹ These crystalline microporous aluminosilicates with 3D channel structures are made of corner-sharing TO₄ tetrahedra (T = Si or Al⁻). Isomorphous framework Al/Si substitutions result in a negative charge of AlO₄⁻ tetrahedra, which is balanced by extra-framework cationic species representing active sites for numerous redox- or base-catalyzed reactions.

The cations can occupy extra-framework sites in silicon-rich zeolites which differ in the coordination, arrangement of the near environment, and location in zeolite channels.¹ These properties are controlled by the siting of the Al atoms of the negatively charged AlO_4^- tetrahedra in the framework crystallographic T sites. There are properties of silicon-rich zeolites, which strongly limit the applicability of diffraction methods to determine the siting of cations: (i) a medium (*e.g.* ferrierite (4) and mordenite (4)) or high (*e.g.* MCM-22 (8), the beta zeolite (9), and ZSM-5 (12 or 24)) number of crystallographically distinguishable framework T sites of which only some are partly occupied by Al atoms, (ii) low number of Al atoms in the framework (Si/Al > 8), and (iii) large unit cells.²

Therefore the knowledge regarding the siting of cations and the local structure of cationic sites in silicon-rich zeolites is very limited.^{1,3} However, this knowledge is essential to evaluate the catalytic and sorption properties of cation exchanged zeolites. Scarce crystallographic studies deal with monovalent cations,^{4–6} but the studies are rather limited to heavy ions (Cs⁺ (ref. 7–9) and Tl⁺ (ref. 10)) not very attractive for catalysis. Li is a very light element which is hardly detected by X-ray diffraction in silicon-rich zeolites employing powder diffraction, and therefore, neutron diffraction was used to detect the siting of Li⁺ ions in silicon-rich matrixes.⁵

The siting of divalent metal cations was determined by X-ray crystallography for ferrierites^{11,12} with Si/Al 8.5 and mordenites,³ while for zeolites with a lower Al content in the framework a methodology based on the Vis spectra of Co²⁺ ions was developed.^{1,13–15} Moreover, X-ray experiments provide only the positions of cations in the framework but not the local structure of the cationic sites as the coordinates of the cations are combined with the averaged coordinates of the framework reflecting mainly empty cationic sites and also the corresponding siliceous structures (*i.e.*, without the framework Al/Si substitutions). Conversely, ^{6,7}Li MAS NMR spectroscopy represents a powerful tool to identify Li⁺ siting.^{16–19} The issue of incorporation of Li⁺ ions into various matrixes has attracted particular attention due to its crucial importance in various fields such as, for example, energy storage²⁰ and CO₂ capture.²¹

In this communication, we demonstrate a new approach to the determination of the siting of Li⁺ and the local structure of Li⁺ sites in the crystalline aluminosilicate matrixes based on the ⁷Li–⁷Li correlation MAS NMR spectroscopy in tandem with periodic DFT calculations of the structure of Li⁺ sites and subsequent DFT cluster computations of the structure of Li⁺ sites and subsequent DFT cluster computations of the ⁷Li NMR shielding. The calculations of the structure include extensive molecular dynamics conformational sampling of the siting of Li⁺ ions. The Li⁺ siting and its variability in silicon-rich ferrierites (Si/Al ≥ 20) is determined and subsequently independently verified using the previous results regarding the Al siting in the same ferrierite samples.²²

The significant differences between the 7 Li MAS NMR spectra (Fig. S1, ESI⁺) clearly reflect the variations in the Li⁺ siting caused by

^a J. Heyrovský Institute of Physical Chemistry, The Czech Academy of Sciences,

Dolejškova 3, CZ 182 23 Prague 8, Czech Republic. E-mail: stepan.sklenak@jh-inst.cas.cz ^b Department of Inorganic Technology, Faculty of Chemical Technology,

University of Pardubice, Doubravice 41, Pardubice, CZ 532 10, Czech Republic

^c Institute of Macromolecular Chemistry, The Czech Academy of Sciences,

Heyrovsky sq. 2, Prague 6, CZ 162 06, Czech Republic

[†] Electronic supplementary information (ESI) available: Details regarding (i) sample preparation and characterization, (ii) ⁷Li NMR experiments, (iii) computational models and methods and (iv) ⁷Li MAS NMR spectra sections. See DOI: 10.1039/c5cc01830g

the different siting of Al atoms in the framework T sites.²² However, a detailed analysis of these spectra is limited due to the narrow range of the 7Li chemical shifts23 and low resolution of 7Li MAS NMR spectra. Zeolites are typical materials for which the broadening of NMR resonances (e.g. for ²⁹Si and ²⁷Al) can originate from the variability of middle- and long-range orderings of the zeolite framework due to isomorphous substitutions of Al into the silicate framework. The observed NMR signal therefore represents a Gaussian envelope of a number of close NMR resonances.²⁴⁻²⁷ The observed ⁷Li broadening is due to neither the anisotropy of the chemical shift nor weak quadrupolar interaction.²³ In this case, the application of ⁶Li MAS NMR spectroscopy (not shown in the figures) does not result in the increase of the spectral resolution. Thus, also the application of an ultra-high field does not represent a viable route to increase the spectral resolution. Multiple quantum (MQ) MAS NMR experiments, which provide a significant increase of the spectral resolution for quadrupolar nuclei, cannot be applied on ⁷Li either due to the small quadrupolar interaction of ⁷Li nucleus.²³ Our experiments show that also applications of various one-dimensional MAS NMR pulse sequences (solid echo, ¹H decoupled single-pulse, and triple-quantum filtered MAS NMR experiments) do not result in the increase of the resolution of the ⁷Li MAS NMR spectra (not shown in the figures). In contrast, we show that analysis of non-diagonal cross-peaks in the 2D ⁷Li-⁷Li correlation spectra²⁸⁻³¹ provides an increase of the spectral resolution and thus the accuracy of the estimation of the number of ⁷Li NMR resonances (Fig. 1).

As the long-range ${}^{7}\text{Li}{}^{-7}\text{Li}$ correlations are evolved during the mixing period (50 ms), the cross-sections through the shoulders apparent in the skyline projections allow refinement of ${}^{7}\text{Li}$ isotropic chemical shifts of the dipolarly coupled partners. Our preliminary calibration tests indicated that the upper limit of ${}^{7}\text{Li}{}^{-1}\text{Li}$ distances that can be effectively probed by the applied correlation experiment is *ca.* 4.0–4.3 Å.

The ⁷Li NMR resonances identified for FER/20–FER/30 using the ⁷Li–⁷Li correlation experiments are shown in Table 1 and Fig. 2. The latter also depicts the relative concentrations of the Li⁺ ions corresponding to the individual ⁷Li NMR resonances obtained by the simulation of ⁷Li MAS NMR spectra employing the ⁷Li chemical shifts from the ⁷Li–⁷Li correlation experiments.

Periodic DFT calculations including molecular dynamics conformational sampling of all possible Li⁺ sites for Al(T1a),²² Al(T1b),²² Al(T2), Al(T3), and Al(T4) yield two low energy (i.e., their relative energy ≤ 2.0 kcal mol⁻¹ with respect to the most stable Li⁺ site for Al in a particular T site) Li⁺ sites for T1 and T2 while only one for T3 and T4. The Li^+ sites for Al(T1a)²² and Al(T1b)²² are the same. Subsequently the ⁷Li NMR shieldings are calculated using seven shell clusters cut out from the optimized structures and converted into ⁷Li chemical shifts (Fig. 2). This combination of employing periodic DFT for the structure determination and cluster DFT for the evaluation of the NMR shielding, which is a local property, has been successfully used in our prior study.²² The calculated relative energies of the other Li⁺ sites are significantly higher and therefore they are not populated.³² The optimized structures of the low energy Li⁺ sites together with the relative energies and the corresponding ⁷Li chemical shifts are shown in Fig. 3.



Fig. 1 2D projection of ⁷Li-⁷Li correlation MAS NMR spectrum of the dehydrated FER/20 (top), FER/27 (middle), and FER/30 (bottom) samples, spectrum projection, selected slices, and marked positions of non-diagonal cross-peaks.

Table 1 Chemical shift in ppm of the $^7{\rm Li}$ NMR resonances of the dehydrated FER/20-FER/30 samples

Sample	⁷ Li NMR resonances (ppm)					
	R1	R2	R3	R4	R5	<i>R</i> 6
FER/20		-0.23		-0.80	-1.07	
FER/27	0.17	-0.20		-0.80	-1.05	
FER/30	0.12		-0.55	-0.85		-1.50

Our computational results show that Li^+ ions are coordinated to two O atoms (only one O atom for the T2A site) of the



Fig. 2 Experimental ⁷Li chemical shifts and their intensities in the spectra of the dehydrated FER/20–FER/30 samples, ⁷Li chemical shifts calculated for Li⁺ ions balancing Al atoms in the T1–T4 sites, and their assignments to the experimental data. FER/20 (**J**), FER/27 (**J**), and FER/30 (**J**); Li⁺ balancing Al in the T1 (**J**), T2 (**J**), T3 (**J**), and T4 (**J**) sites.



Fig. 3 Optimized structures (Li–O distances in Å) with the designations of the T sites of the low energy Li⁺ sites (T1A and T1B for Al(T1), T2A and T2B for Al(T2), T3A for Al(T3), and T4A for Al(T4)), the relative energies in kcal mol⁻¹, and the corresponding ⁷Li chemical shifts in ppm converted using the ⁷Li NMR shielding of 90.16 ppm for Li⁺(H₂O)₄ with the ⁷Li chemical shift at 0.00 ppm.³³ Silicon atoms are in gray, oxygen atoms in red, aluminum atoms in yellow, and lithium in violet.

 AlO_4^- framework (Li– O_{Al} distances from 1.88 to 2.01 Å) and up to two O atoms of the SiO₄ framework (Li– O_{Si} distances from 2.04 to 2.45 Å) in dehydrated zeolites and that the Li⁺ siting is controlled by the location of Al atoms in the framework T sites. Two Li⁺ sites are occupied concurrently for Al(T1) and Al(T2) while only one for Al(T3) and Al(T4).

Fig. 2 compares the experimental ⁷Li chemical shifts with the calculated ones. The patterns of the experimental and predicted ⁷Li chemical shifts in Fig. 2 show significant similarities. The R5 resonance observed for the FER/20 and FER/27 samples (Table 1) can be safely assigned to the T2A site. Since there are two low energy Li^+ sites for Al(T2), the R2 resonance measured for the same samples corresponds to the T2B site. Then, it follows that the *R*4 resonance observed also for FER/20 and FER/27 belongs to either one of the T3A and T4A sites or to both of them. The calculated ⁷Li chemical shifts of T3A and T4A are too close to each other to be distinguishable by ⁷Li MAS NMR spectroscopy. The R1 resonance observed for FER/27 and FER/30 can be safely assigned to the T1A site. There are three more ⁷Li NMR resonances measured for FER/30 (Table 1). R4 corresponds to either one of the T3A and T4A sites or to both of them while R3 belongs to the T1B site which is the other low energy Li⁺ site for Al(T1). Fig. 2 shows the assignment of the observed ⁷Li NMR resonances to the Li⁺ sites. The shift deviations are *ca*. ± 0.2 ppm. The remaining very low intensity *R*6 resonance at -1.50 ppm, which is observed only for FER/30, cannot be assigned to any of the calculated low energy Li⁺ sites and its origin is unknown. The ranges of the observed (without the unassigned *R*6) and calculated ⁷Li chemical shifts (1.24 and 1.18 ppm, respectively) are in very good agreement.

There are no experimental data based on diffraction methods regarding the siting of Li⁺ in ferrierites. However, the knowledge of the Al siting in the three ferrierite samples used²² permits a verification of the siting of Li⁺ ions obtained in this study. The Al atoms occupy the T sites in the samples (for details see Fig. 6 of ref. 22) as follows: T2, T3, and T4 in FER/20; T1, T2, T3, and T4 in FER/27; and T1, T3, and T4 in FER/30. Fig. 4 compares the relative concentration of Al atoms (in %) corresponding to the T sites obtained from (i) the corresponding Li⁺ siting analyzed using ⁷Li MAS NMR and (ii) ²⁷Al MAS NMR experiments.²²

The agreement between the results obtained by ⁷Li and ²⁷Al MAS NMR is very good and confirms the assignment of the experimental ⁷Li NMR resonances to the Li⁺ sites related to Al in the individual T sites. It substantiates that the siting of Li⁺ is controlled by the siting of Al atoms in the zeolite framework. Moreover, the agreement supports the reliability of (i) the periodic DFT calculations of the local structure of Li⁺ sites using extensive conformational sampling and (ii) DFT cluster computations of the ⁷Li NMR shielding. Moreover, only the ²⁷Al 3Q MAS NMR experiments allow the distinction between the T3 and T4 sites and reveal that the ⁷Li R4 resonance observed for all the three samples belongs to Li⁺ in both the T3A and T4A sites. Therefore, the combination of ⁷Li MAS NMR and ²⁷Al 3Q MAS NMR experiments in tandem with DFT calculations is suggested to represent the optimal approach to the analysis of the Al and Li⁺ sitings in the framework T and extra-framework sites, respectively, in silicon-rich zeolites.

Li⁺ ions in many crystalline oxides are assigned to tetrahedral and octahedral sites based on their ⁶Li chemical shifts.³⁴ According to ⁶Li chemical shift correlation data,³⁵ Li⁺ ions in the former and latter positions exhibit positive and negative ⁶Li



Fig. 4 Relative concentration of Al atoms (in %) corresponding to the distinguishable framework T sites obtained from (i) the corresponding Li⁺ siting analyzed using ⁷Li MAS NMR and (ii) ²⁷Al MAS NMR.²²

chemical shifts, respectively. However, our study on a siliconrich zeolite reveals that the coordination of Li⁺ ions (also showing positive and negative 7Li chemical shifts) exhibits low symmetry and it is different from tetrahedral or octahedral. The local structure of Li⁺ sites is controlled by the framework structure and by the location of Al atoms in the framework T sites.

In summary, we present a newly developed method to determine the siting of Li⁺ and the local structure of Li⁺ sites in crystalline aluminosilicate matrixes based on a combination of ⁷Li-⁷Li correlation MAS NMR spectroscopy and periodic DFT calculations of the structure of Li⁺ sites and subsequent DFT cluster computations of the ⁷Li NMR shielding. The developed approach can be in general applied to Li⁺ ions in other zeolites and various crystalline matrixes with large unit cells and a low concentration of Li⁺ and also to other NMR-active cations without a significant limitation of their concentration. It should be stressed that calculations with an extensive conformational sampling of the cation are required (due to the absence of experimental data regarding the siting of the cation) to obtain the accurate siting of the cation, *i.e.* employing only optimizations of the structure of the cationic sites in the zeolite framework is not sufficient.

This work was supported by the Grant Agency of the Czech Republic (# GA 15-14007S), COST Action MP1202 HINT (Ministry of Education, Youth and Sports LD14010) and the RVO:61388955 and RVO:61389013. This work was supported by the IT4Innovations Centre of Excellence project (CZ.1.05/1.1.00/02.0070), funded by the European Regional Development Fund and the national budget of the Czech Republic via the Research and Development for Innovations Operational Programme, as well as Czech Ministry of Education, Youth and Sports via the project Large Research, Development and Innovations Infrastructures (LM2011033).

Notes and references

- 1 J. Dedecek, Z. Sobalik and B. Wichterlova, Catal. Rev., 2012, 54, 135 - 223.
- 2 http://www.iza-structure.org/databases.
- 3 W. J. Mortier, Extraframework cationic positions in zeolites, Elsevier, Amsterdam, 1982.
- 4 I. J. Pickering, P. J. Maddox, J. M. Thomas and A. K. Cheetham, J. Catal., 1989, 119, 261-265.
- 5 B. F. Mentzen, J. Phys. Chem. C, 2007, 111, 18932-18941.
- 6 B. F. Mentzen and G. Bergeret, J. Phys. Chem. C, 2007, 111, 12512-12516.
- 7 D. H. Olson, N. Khosrovani, A. W. Peters and B. H. Toby, J. Phys. Chem. B, 2000, 104, 4844-4848.
- 8 B. F. Mentzen, G. Bergeret, H. Emerich and H. P. Weber, J. Phys. Chem. B, 2006, 110, 97-106.
- 9 C. W. Kim, N. H. Heo and K. Seff, J. Phys. Chem. C, 2011, 115, 24823-24838.
- 10 N. H. Heo, C. W. Kim, H. J. Kwon, G. H. Kim, S. H. Kim, S. B. Hong and K. Seff, J. Phys. Chem. C, 2009, 113, 19937-19956.
- 11 M. C. Dalconi, G. Cruciani, A. Alberti, P. Ciambelli and M. T. Rapacciuolo, Microporous Mesoporous Mater., 2000, 39, 423-430.
- 12 M. C. Dalconi, A. Alberti, G. Cruciani, P. Ciambelli and E. Fonda, Microporous Mesoporous Mater., 2003, 62, 191-200.
- 13 J. Dedecek and B. Wichterlova, J. Phys. Chem. B, 1999, 103, 1462–1476. 14 D. Kaucky, J. Dedecek and B. Wichterlova, Microporous Mesoporous
- Mater., 1999, 31, 75-87. 15 S. Sklenak, P. C. Andrikopoulos, S. R. Whittleton, H. Jirglova, P. Sazama, L. Benco, T. Bucko, J. Hafner and Z. Sobalik, J. Phys. Chem. C, 2013, 117, 3958-3968.
- 16 M. Feuerstein and R. F. Lobo, Chem. Mater., 1998, 10, 2197-2204.
- 17 L. J. Smith, H. Eckert and A. K. Cheetham, J. Am. Chem. Soc., 2000,
- 122, 1700-1708. 18 L. J. Smith, H. Eckert and A. K. Cheetham, Chem. Mater., 2001, 13, 385-391.
- 19 H. Oka, S. Kasahara, T. Okada, S. Yoshida, A. Harada, H. Ohki and T. Okuda, Microporous Mesoporous Mater., 2002, 51, 1-5.
- 20 M. Armand and J. M. Tarascon, Nature, 2008, 451, 652-657.
- 21 T. D. Pham, Q. Liu and R. F. Lobo, Langmuir, 2013, 29, 832-839.
- 22 J. Dedecek, M. J. Lucero, C. Li, F. Gao, P. Klein, M. Urbanova, Z. Tvaruzkova, P. Sazama and S. Sklenak, J. Phys. Chem. C, 2011, 115, 11056-11064.
- 23 K. J. D. Mackenzie and A. M. E. Smith, Multinuclear Solid State NMR of Inorganic Materials, Elsevier, 2002.
- C. A. Fyfe, G. C. Gobbi, J. Klinowski, J. M. Thomas and S. Ramdas, 24 Nature, 1982, 296, 530-533.
- 25 S. Sklenak, J. Dedecek, C. B. Li, B. Wichterlova, V. Gabova, M. Sierka and J. Sauer, Angew. Chem., Int. Ed., 2007, 46, 7286-7289.
- 26 S. Sklenak, J. Dedecek, C. Li, B. Wichterlova, V. Gabova, M. Sierka and J. Sauer, Phys. Chem. Chem. Phys., 2009, 11, 1237-1247.
- 27 J. Dedecek, S. Sklenak, C. Li, F. Gao, J. Brus, Q. Zhu and T. Tatsumi, J. Phys. Chem. C, 2009, 113, 14454-14466.
- 28 L. S. Cahill, Y. Iriyama, L. F. Nazar and G. R. Goward, J. Mater. Chem., 2010, 20, 4340-4346.
- 29 H. Hain, M. Scheuermann, R. Heinzmann, L. Wuensche, H. Hahn and S. Indris, Solid State Nucl. Magn. Reson., 2012, 42, 9-16.
- 30 Y.-Y. Hu, Z. Liu, K.-W. Nam, O. J. Borkiewicz, J. Cheng, X. Hua, M. T. Dunstan, X. Yu, K. M. Wiaderek, L.-S. Du, K. W. Chapman, P. J. Chupas, X.-Q. Yang and C. P. Grey, Nat. Mater., 2013, 12, 1130-1136.
- 31 A. Kuhn, S. Dupke, M. Kunze, S. Puravankara, T. Langer, R. Poettgen, M. Winter, H.-D. Wiemhoefer, H. Eckert and P. Heitjans, J. Phys. *Chem. C*, 2014, **118**, 28350–28360. 32 By 3–7 kcal mol⁻¹ for Al(T1), 5–6 kcal mol⁻¹ for Al(T2), 5–6 kcal mol⁻¹ for
- AI(T3), and 12–19 kcal mol⁻¹ for Al(T4).
- 33 The calculated NMR shielding values are as follows: 89.84 ppm (T1A), 90.50 ppm (T1B), 91.02 ppm (T2A), 90.61 ppm (T2B), 90.94 ppm (T3A), and 90.87 ppm (T4A).
- 34 M. Vijayakumar, S. Kerisit, K. M. Rosso, S. D. Burton, J. A. Sears, Z. G. Yang, G. L. Graff, J. Liu and J. Z. Hu, J. Power Sources, 2011, 196, 2211-2220.
- 35 Z. Xu and J. F. Stebbins, Solid State Nucl. Magn. Reson., 1995, 5, 103 - 112.